

Frosted Sheet

VIVAK® VF Frost Sheet is a low gloss smooth finish translucent copolyester product. This material features improved toughness versus acrylic and maintains a low gloss surface after thermoforming. VIVAK VF Frost sheet has the appearance of etched glass and diffuses light, enhancing design options.


Applications

Point of purchase displays, slatwall fixtures, interior architectural elements and interior decorative glazing

Typical Properties			
Properties	Test Method	Units	Values
PHYSICAL			
Specific Gravity	ASTM D792	-	1.27
Water Absorption, 24 hours	ASTM D570	%	0.2
Light Transmission @ 0.118"	ASTM D1003	%	82
MECHANICAL			
Tensile Strength, Ultimate	ASTM D638	psi	7,700
Tensile Modulus	ASTM D638	psi	301,000
Flexural Strength	ASTM D790	psi	11,400
Flexural Modulus	ASMT D790	psi	351,000
Shear Strength	ASTM D732	psi	4,070
Compressive Strength	ASTM D895	psi	7,250
Instrumented Impact	ASTM D3763	ft-lb	22
Rockwell Hardness	ASTM D785	R Scale	115
Izod Impact Notched 0.125" @ 73°F	ASTM D256	ft/lbs	1.0
Izod Impact Notched 0.125" @ 32°F	ASTM D256	ft/lbs	0.8
THERMAL			
Heat Deflection Temperature, @ 264 psi	ASTM D648	°F	157
Heat Deflection Temperature, @ 66 psi	ASTM D648	°F	164
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.8 x 10 ⁻⁵
Glass Transition Temperature	ASTM D3418	°F	178

Disclaimer

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by us. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.



Sheffield Plastics
A Bayer MaterialScience LLC Business

119 Salisbury Road
Sheffield, MA 01257
800-254-1707
FAX: 800-457-3553
Website: sheffieldplastics.com
E-mail: info@sheffieldplastics.com